

Proper opgelost.

TECHNICAL SPECIFICATION

NOVOCLEAN 940MCW

No	Inspection Items	Unit	Result
1	Weight	g/sqm	320
2	Thickness	mm	2.01
3	Shrinkage after washing	%	MD: 2.9
			CD: 1.4
4	Tensile Strength	kgf	MD: 15
			CD: 14.5
5	Elongation	%	MD: 100
			CD: 76
6	Total absorption	wt%	500

※ Note

1. Test Method : KS K 0210 Testing methods for quantitative analysis of fiber mixtures
 3. Water Temperature: 60°C, Dry : Tumble Dry
Extension: -
 6. Total Absorption(%)= (Wet Weight- Dry Weight)/Dry Weight*100
- * MD : Machine direction, CD: Cross direction